




FRICITION TEST FOR BRAKE LINING
SAE J 661 (modified)



MATERIAL : LT/867

APPLICATION: Industrial equipments




Updated: Apr/01

Specific gravity: 1.20 g/cm³

Gogan hardness: -

Wear data

	Thickness, mm	Weight, g
Start	-	-
Finish	-	-
Loss	<u>0.45</u>	<u>0.25</u>
% lost	<u>7.15</u>	<u>5.95</u>



Wear test 400 °F/204°

0.25 mm

Remarks

Typical friction level

Normal 0.510 G

Hot 0.450 F

Ref. NO.: EF 90.065

Controlled: Physical Lab