



PROCEDIMENTO DE CONTROLE DA QUALIDADE DE GUARNIÇÕES PARA FREIOS
BRAKE LINING QUALITY CONTROL TEST PROCEDURE

SAE J 661a - NBR 5541

MATERIAL: LA/201

LOTE: _____

Programa Nº: _____
Program. No.

Máquina Nº: _____
Machine No.

Operador: _____
Operator

Visto: _____
Visa

M.ESPECÍFICA (NBR 5544): _____ **1,79** g/cm³
Specific Gravity

DUREZA (NBR 5520): _____ **45** GC
Hardness

**DESGASTE
Wear Data**

Espessura, mm Peso, gr
Thickness Weight

INICIAL: _____
Start

FINAL: _____
Finish

PERDA: **0,38** **0,460**
Loss

_____ %

ENSAIO DESGASTE 204 °C: _____ **0,30** mm
Wear Test 400 °F

TAXA DESGASTE 204 °C: _____ cm³/Kwh
Wear Rate 400 °F



COEFICIENTE DE ATRITO: _____
Coefficient of Friction

NORMAL: _____ **0,500 G**
Normal

QUENTE: _____ **0,460 G**
Hot

ENSAIO Nº: _____ DATA: _____
Test No. Date

nov/02



OBSERVAÇÕES:
Remarks
